

SPECIFICATION MICROOVERLAY ISOPLAM®

| Art. Working Stages | Workplace Description | Indicative estimated quantity |
|-------------------------------------|---|--|
| Art. 1 Support Preparation | <p>Depending on the support's type and conditions, the surface shall be treated differently: polishing, shot-peening or using ISOPLAM® GROUT REMOVER.</p> <p>Possible cracks on the surface shall be recovered with ISOPLAM® IPM EPOXY KIT TIXO, a thixotropic plaster.</p> <p>Remove of all the dust caused by the support preparation.</p> | |
| | <p>Laying of ISOPLAM® VAPOR BARRIER, together with ISOPLAM® FIBERGLASS NET in case of rising damp or in case of non-uniform absorption of the surface.</p> <p>Application by roller or by brush of the quartz clinging ISOPLAM® DECO PRIMER FINISH on those supports where the use of ISOPLAM® VAPOR BARRIER is not necessary.</p> | <p>1,50 kg/m²</p> <p>0,150 kg/m²</p> |
| Art. 2 ISOPLAM® MICROOVERLAY | <p>Application of the first coat of ISOPLAM® MICROOVERLAY BASE or MEDIUM, mixed with the acrylic polymer ISOPLAM® MICROOVERLAY LIQUID POLYMER and with ISOPLAM® PLAM COLOR according to the colour chosen (see ISOPLAM® MICROOVERLAY COLOR CHART).</p> <p>As the surface completely dries, sand with ISOPLAM® FLOOR BUFFER and ISOPLAM® SANDPAPER DISC.</p> <p>Vacuum of all residual dusts.</p> <p>Application of the second coat of ISOPLAM® MICROOVERLAY MEDIUM to be mixed with the acrylic polymer ISOPLAM® MICROOVERLAY LIQUID POLYMER and with ISOPLAM® PLAM COLOR according to the colour chosen (see ISOPLAM® MICROOVERLAY COLOR BOX).</p> <p>As the surface completely dries, sand with ISOPLAM® FLOOR BUFFER and ISOPLAM® SANDPAPER DISC.</p> <p>Vacuum of all residual dusts.</p> <p>Application of the finishing coat of ISOPLAM® MICROOVERLAY MEDIUM or FINISH (depending on the desired effect), to be mixed with with the acrylic polymer ISOPLAM® MICROOVERLAY LIQUID POLYMER and with ISOPLAM® PLAM COLOR according to the colour chosen (see ISOPLAM® MICROOVERLAY COLOR BOX).</p> <p>As the surface completely dries, sand with ISOPLAM® FLOOR BUFFER and ISOPLAM® SANDPAPER DISC.</p> <p>Vacuum of all residual dusts.</p> | |

| | | |
|--|---|--|
| <p>Art. 3 ISOPLAM® PROTECTIVE RESIN TREATMENT</p> | <p>Application of two coats of protective solvent-based resin ISOPLAM® PLAM POL, or water-based ISOPLAM® PLAM POL WATER. Choosing the right protective resin is essential and it depends on the type of traffic and use destination of the surface.</p> <p>Application of ISOPLAM® METALLIC WAX, with the use of a ISOPLAM® WAX SPREADER.</p> | <p>0,200 kg/m²</p> <p>50 gr/m²</p> |
|--|---|--|



| <i>Unitary Expense</i> |
|----------------------------|
| |
| |
| |

